



### Product Information

Plasticized PVC (PVC-P) transparent granulates.

There are stabilized by Ca-Zn heat stabilizer system and homogenously processed plasticizer DEHP. There aren't recommended for use in medical products, toys, and food packaging applications. There are containing no heavy metals.

There are specified for inside applications, are applicable for extrusion, injection molding, pressing.

Packaging: Granulates are delivered in 25 kg PE-bags placed on wooden pallets (1000 kg) or in big-bag.

### TECHNICAL SPECIFICATION

Properties	Unit	Guaranteed value	Standard
Heat stability at 200°C, min. (Kongo)	min	20	ISO 182-1
Density	g.cm <sup>-3</sup>	1,22-1,26	EN ISO 1183
Hardness	Shore A	82-86	EN ISO 868