

Product Information

Unplasticized PVC (PVC-U) granulates. There are stabilized by Ca-Zn heat stabilizer system and UV stabilizer (middle), they contain no heavy metals. There are specified for inside application with occasional UV exposition.

It is applicable for profiles extrusion.

The colour tone – the number of colour tone is stated in Trademark of the granulate (behind the slash) e.g.: Tiulit TCL 03/12 white.

- no colour - n.0, n.05
- white - n.12
- light grey - n.2, ca RAL 7035
- grey - n.23, ca RAL 7042
- black - n.9

Packaging: Granulates are delivered in 25 kg PE-bags placed on wooden pallets (1000 kg) or in big-bag.

TECHNICAL SPECIFICATION

Properties	Unit	Guaranteed value	Standard
Heat stability at 200°C, min. (Kongo)	min	20	ISO 182-1
Charpy Impact test unnotched, +23°C	kJ.m^{-2}	no break	EN ISO 179-1
Charpy Impact test notched, +23°C, V-notch	kJ.m^{-2}	4	EN ISO 179-1
Colour tone		According to standard	